

XENOY™ RESIN HX5600HP

REGION ASIA

DESCRIPTION

Xenoy HX5600HP is PBT based semi-crystalline blend with balanced flow and impact properties. Improved chemical resistance against lab disinfectants and chemicals for healthcare enclosure and housing applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO, Gamma and Steam sterilizable.

TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	50	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	52	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	150	%	ASTM D 638
Tensile Modulus, 5 mm/min	2100	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	70	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2000	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	100	%	ISO 527
Tensile Modulus, 1 mm/min	2050	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	2050	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	750	J/m	ASTM D 256
Izod Impact, notched, -30°C	600	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	80	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 -40°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	55	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	25	kJ/m ²	ISO 180/1A
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	60	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	125	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, flow	1.E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	125	°C	ISO 306
Vicat Softening Temp, Rate B/120	123	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Bf

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	80	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.7 – 1.1	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	11	g/10 min	ASTM D 1238
Density	1.22	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.4	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	10	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	260	Pa-s	ISO 11443
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	255 – 270	°C	
Nozzle Temperature	250 – 265	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Middle - Zone 2 Temperature	240 – 265	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	60 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.