

LEXANTM FR RESINS 505R

REGION ASIA

DESCRIPTION

LEXAN 505R Polycarbonate (PC) is an injection moldable non-chlorinated and non-brominated flame retardant grade that is 10% glass fiber filled. It has a UL94 V0@1.5mm rating and is available in various opaque color options. This is an alternative to LEXAN 500, 500R, 500RS, 500ECR.

INDUSTRY	SUB INDUSTRY
Consumer	Sport/Leisure
Electrical and Electronics	Electrical Devices and Displays, Electrical Components and Infrastructure
Healthcare	Healthcare, Patient Testing

TYPICAL PROPERTY VALUES

Revision 20200610

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	63	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	48	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	12	%	ASTM D 638
Tensile Modulus, 5 mm/min	3930	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	108	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3530	MPa	ASTM D 790
Hardness, Rockwell M	85	-	ASTM D 785
Hardness, Rockwell R	124	-	ASTM D 785
Taber Abrasion, CS-17, 1 kg	11	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	60	MPa	ISO 527
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	7	%	ISO 527
Tensile Modulus, 1 mm/min	3300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	3400	MPa	ISO 178
Ball Indentation Hardness, H358/30	115	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched, 23°C	1602	J/m	ASTM D 4812
Izod Impact, notched, 23°C	107	J/m	ASTM D 256
Izod Impact, notched, -30°C	80	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	61	J	ASTM D 3763
Izod Impact, unnotched 80°10°3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10°3 -30°C	130	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°3 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°3 -30°C	8	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80°10°4 +23°C	NB	kJ/m ²	ISO 180/1U

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	10	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	9	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	9	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 23°C	15	kJ/m ²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Specific Heat	1.21	J/g-°C	ASTM C 351
Thermal Conductivity	0.2	W/m-°C	ASTM C177
Vicat Softening Temp, Rate B/50	149	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	143	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	138	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.68E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.46E-05	1/°C	ASTM E 831
Thermal Conductivity	0.21	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	4.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	141	°C	ISO 306
Vicat Softening Temp, Rate B/120	143	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	144	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	136	°C	ISO 75/Ae
HDT/Ae, 1.8 MPa Annealed 120°C, 2hrs	136	°C	ISO 75/Ae
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	135	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	142	°C	ISO 75/Bf
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
PHYSICAL			
Specific Gravity	1.26	-	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.13	%	ASTM D 570
Water Absorption, 24 hours	0.12	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.31	%	ASTM D 570
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.6	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	7	g/10 min	ASTM D 1238
Density	1.25	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.31	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.13	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	7	cm ³ /10 min	ISO 1133

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
ELECTRICAL			
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	33	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.8	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.01	-	IEC 60250
Comparative Tracking Index	175	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.9	-	IEC 60250
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E207780-228398	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	3	mm	UL 94
UL Compliant, 94-5VB Rating	2	mm	UL 94 by SABIC-IP
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
Oxygen Index (LOI)	37	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	290 – 320	°C	
Nozzle Temperature	280 – 310	°C	
Front - Zone 3 Temperature	290 – 320	°C	
Middle - Zone 2 Temperature	280 – 310	°C	
Rear - Zone 1 Temperature	270 – 300	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 120	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.