

# LEXAN™ FR RESIN 945

REGION ASIA

## DESCRIPTION

LEXAN 945 Polycarbonate (PC) resin is a non-filled, injection moldable grade. This non-chlorinated, non-brominated flame retardant PC has an UL-94 V0 rating and is available in various opaque color options. LEXAN 945 is a general purpose resin designed to meet the needs of various applications.

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	125	%	ASTM D 638
Tensile Modulus, 50 mm/min	2270	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	101	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	801	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	73	J	ASTM D 3763
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	143	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	126	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.66E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.66E-05	1/°C	ASTM E 831
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10	g/10 min	ASTM D 1238
<b>ELECTRICAL</b>			
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	3	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-2 Flame Class Rating	0.8	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	1.0	mm	UL 94
UL Recognized, 94-5VA Rating	3.0	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1.0	mm	IEC 60695-2-12

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Glow Wire Ignitability Temperature, 1.0 mm	875	°C	IEC 60695-2-13
Oxygen Index (LOI)	35	%	ISO 4589
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.