

# LNP<sup>TM</sup> VERTON<sup>TM</sup> COMPOUND RVL29XXP

RFL-8029

## DESCRIPTION

LNP VERTON RVL29XXP is a compound based on PA 66 resin, containing Long Glass Fiber, PTFE. Added features include; Internally Lubricated.

## TYPICAL PROPERTY VALUES

Revision 20200306

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, break, 5 mm/min	231	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.3	%	ISO 527
Flexural Stress, yield, 2 mm/min	361	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3.2	%	ISO 178
Flexural Modulus, 2 mm/min	13600	MPa	ISO 178
Flexural Strain, break, 2 mm/min, 60°C	3.6	%	ISO 178
Flexural Strain, break, 2 mm/min, 100°C	3.2	%	ISO 178
Flexural Strain, break, 2 mm/min, 150°C	3.5	%	ISO 178
Flexural Strain, break, 2 mm/min, 200°C	2.7	%	ISO 178
Flexural Stress, yield, 2 mm/min, 60°C	300	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 100°C	256	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 150°C	204	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 200°C	162	MPa	ISO 178
Flexural Modulus, 2 mm/min, 60°C	11700	MPa	ISO 178
Flexural Modulus, 2 mm/min, 100°C	10500	MPa	ISO 178
Flexural Modulus, 2 mm/min, 150°C	9000	MPa	ISO 178
Flexural Modulus, 2 mm/min, 200°C	8900	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, notched 80*10*3 -40°C	28	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	82	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -40°C	74	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	30	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
Specific Heat	1478	J/kg-K	ASTM E 1269
CTE, 23°C to 60°C, flow	2.1E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	4.9E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	258	°C	ISO 75/Af
Thermal Conductivity	0.27	W/m-K	ASTM D 5930
Relative Temp Index, Elec <sup>(1)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	65	°C	UL 746B
<b>PHYSICAL</b>			
Mold Shrinkage, flow, 24 hrs	0.13	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.48	%	ISO 294

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Wear Factor Washer	21	10 <sup>-5</sup> in <sup>3</sup> -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.39	-	ASTM D 3702 Modified: Manual
Static COF	0.4	-	ASTM D 3702 Modified: Manual
Density	1.65	g/cm <sup>3</sup>	ISO 1183
Water Absorption, 23°C/24hrs	1.19	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.46	%	ISO 62
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
UL Yellow Card Link	<a href="#">E45329-101282694</a>	-	-
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
<b>INJECTION MOLDING</b>			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	290 – 305	°C	
Front - Zone 3 Temperature	290 – 300	°C	
Middle - Zone 2 Temperature	290 – 300	°C	
Rear - Zone 1 Temperature	280 – 295	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.