

Product description

(PC+ABS) blend; 15 % mineral filled; flame retardant; V-0 at 1.5 mm (UL 94); high stiffness; tensile modulus 4,600 MPa; Vicat softening temperature (VST/B120) 98 °C

Applications

Injection molding; Housings; Notebooks

Sustainability

Partially bio-circular product attributed via mass balance in accordance with the ISCC PLUS standard. The certified material share is detailed in the sustainability declaration.

Typical Values

Rheological properties

Property	Test Condition	Value	Unit	Standard
Melt Volume-flow Rate (MVR)	240 °C/5 kg	13	cm ³ /10 min	ISO 1133-1
Melt Viscosity	260 °C; 1,000 s ⁻¹	165	Pa·s	b. o. ISO 11443-A
Molding Shrinkage, parallel	150×105×3 mm	0.30 - 0.50	%	b. o. ISO 2577
Molding Shrinkage, normal	150×105×3 mm	0.30 - 0.50	%	b. o. ISO 2577

Mechanical properties (23 °C; 50 % r. h.)

Property	Test Condition	Value	Unit	Standard
Tensile Modulus	1 mm/min	4,600	MPa	ISO 527-1,-2
Yield Stress	50 mm/min	65	MPa	ISO 527-1,-2
Yield Strain	50 mm/min	3	%	ISO 527-1,-2
Stress at Break	50 mm/min	40	MPa	ISO 527-1,-2
Strain at Break	50 mm/min	10	%	ISO 527-1,-2
Flexural Modulus	2 mm/min	4,500	MPa	ISO 178
Flexural Strength	2 mm/min	105	MPa	ISO 178
Izod Impact Strength	23 °C	72	kJ/m ²	ISO 180/U
Izod Notched Impact Strength	23 °C	6	kJ/m ²	ISO 180/A

Thermal properties

Property	Test Condition	Value	Unit	Standard
Temperature of Deflection under Load (HDT)	1.80 MPa	85	°C	ISO 75-1,-2
Temperature of Deflection under Load (HDT)	0.45 MPa	92	°C	ISO 75-1,-2



Property	Test Condition	Value	Unit	Standard
Vicat Softening Temperature	50 N; 50 °C/h	96	°C	ISO 306
Vicat Softening Temperature	50 N; 120 °C/h	98	°C	ISO 306
Coefficient of Linear Thermal Expansion (CLTE), parallel	23 to 55 °C	0.46	10 ⁻⁴ /K	ISO 11359-1,-2
Coefficient of Linear Thermal Expansion (CLTE), normal	23 to 55 °C	0.63	10 ⁻⁴ /K	ISO 11359-1,-2
Burning Behavior	1.2 mm; BK, GY	V-0		UL 94
Burning Behavior	1.5 mm	V-0		UL 94

Burning Behavior: BK = black, BL = blue, CL = clear, GY = gray, NC = natural color, RD = red, TL = translucent, WT = white, YL = yellow

Electrical properties (23 °C; 50 % r. h.)

Property	Test Condition	Value	Unit	Standard
Relative Permittivity	100 Hz	3.1		IEC 60250
Relative Permittivity	1 MHz	3.0		IEC 60250
Dielectric Dissipation Factor	100 Hz	50	10 ⁻⁴	IEC 60250
Dielectric Dissipation Factor	1 MHz	70	10 ⁻⁴	IEC 60250
Volume Resistivity		1E14	Ω·m	IEC 62631-3-1
Surface Resistivity		1E16	Ω	IEC 62631-3-2
Electric Strength	1 mm	35	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI)	Solution A	275	V	IEC 60112

Other properties (23 °C)

Property	Test Condition	Value	Unit	Standard
Water Absorption (Saturation Value)	Water at 23 °C	0.5	%	ISO 62
Water Absorption (Equilibrium Value)	23 °C; 50 % r. h.	0.2	%	ISO 62
Density		1,280	kg/m ³	ISO 1183-1

Processing conditions for test specimens

Property	Test Condition	Value	Unit	Standard
Injection Molding - Melt Temperature		240	°C	ISO 294-1
Injection Molding - Mold Temperature		80	°C	ISO 294-1
Injection Molding - Injection Velocity		240	mm/s	ISO 294-1

Recommended processing and drying conditions

Property	Test Condition	Value	Unit	Standard
Dry Air Drying Temperature		80	°C	
Dry Air Drying Time		4	h	
Moisture Content max. (%)		≤ 0.02	%	



Property	Test Condition	Value	Unit	Standard
Melt Temperatures		240 - 270	°C	
Standard Melt Temperature		260	°C	
Barrel Temperatures	Rear	220 - 230	°C	
Barrel Temperatures	Middle	225 - 235	°C	
Barrel Temperatures	Front	230 - 240	°C	
Barrel Temperatures	Nozzle	255 - 265	°C	
Mold Temperatures		60 - 80	°C	
Hold Pressure (% of Injection Pressure)		50 - 75	%	
Plastic Back Pressure (specific)		50 - 150	bar	
Peripheral Screw Speed		0.05 - 0.2	m/s	
Shot-to-Cylinder Size		30 - 70	%	
Vent Depth		0.025 - 0.075	mm	

Health and Safety Information

Before working with this product, you must read and become familiar with the available information regarding its risks, proper use, and safe handling. This information is provided in various formats, including the current Safety Data Sheet (SDS) and product label. SDS can be accessed via the following link:

[Safety Data Sheets \(SDS\) for Covestro products | Covestro](#)

For further questions, please use the contact information provided on this technical data sheet.

Please note that for products manufactured in different colors, safety data may vary depending on the color variant.

Disclaimer

Responsibility and Liability

The use of Covestro products, technical assistance, and information (regardless of how provided) is outside Covestro's control and is solely the responsibility of the customer. The customer must conduct adequate testing to determine the suitability of products for its intended use, including but not limited to technical, health, safety, and environmental aspects. Unless otherwise agreed in writing, all products are sold exclusively under Covestro's standard conditions of sale, which prevail in case of conflict and are available upon request.

The terms and conditions of sale and delivery are available via the following link:

<https://order.covestro.com/covestrostorefront/saleConditions>

All information is provided "as is" without warranties, express or implied, including merchantability or fitness for a particular purpose, and is subject to change without notice. To the maximum extent permitted by law, Covestro disclaims, and the customer assumes all liability for losses, damages, or claims arising out of use of Covestro products, technical assistance, or information. Any statement or recommendation not expressly contained in Covestro documentation is unauthorized and shall not bind Covestro. Nothing herein shall be construed as encouraging or recommending the use of any product in conflict with any claim of any patent. No license is implied or in fact granted under the claims of any patent.



Restrictions on Regulated Applications

This product is not intended for use in regulated applications such as agriculture, cosmetics, drinking water contact, food contact, medical products (e.g., medical devices), toys, or similar uses subject to specific regulatory requirements. Prior written approval from Covestro is required before this product may be used in any regulated application. The customer is solely responsible for ensuring compliance with all applicable laws and determining product suitability. Covestro disclaims all liability and warranties for unauthorized regulated uses.

Typical Value

These values are provided as typical data only and do not constitute binding specifications or warranted performance, unless explicitly agreed by Covestro in writing. Performance may vary depending on factors including, but not limited to, mold/die, processing conditions and coloring/pigmentation. Unless otherwise stated, values are based on standardized test specimens at room temperature.

Sample

Samples provided by Covestro are intended solely for evaluation and testing purposes by the customer and may not be used in commercial applications, resold, transferred to third parties (except qualified testing service providers acting on behalf of the customer), reverse engineered, modified, or used in any manner not explicitly authorized in writing by Covestro. Samples are provided 'as-is' without any warranties, express or implied, including fitness for a particular purpose. Customers are solely responsible for ensuring safe handling, regulatory compliance, and suitability of the material for their intended evaluations. Covestro disclaims all liability for damages or losses arising from the use of samples.

Shrinkage

Shrinkage data is provided for reference only and is based on plaques molded under specific, controlled processing conditions. Actual shrinkage values in production parts may vary due to numerous factors, including but not limited to part design (e.g., size, thickness, geometry), mold design (e.g., gate type and location, runner design, mold materials, cooling system), and molding conditions (e.g., processing temperature, mold temperature, packing time and pressure, injection speed).

The determination and application of shrinkage values are the sole responsibility of the customer and must be based on their own testing and experience under actual production conditions. To the maximum extent permitted by law, Covestro shall not be liable for any damages, losses, or claims arising from the use of, or reliance on, the shrinkage data provided.

Recommended Processing and Drying Conditions

The recommended processing and drying conditions are provided for reference only and do not constitute binding specifications or warranted values. Barrel temperatures are based on a standard 3-zone barrel; other configurations may require different settings. Values for hold pressure as a percentage of injection pressure may vary depending on part geometry, injection molding machine, and injection mold. Drying conditions are specified for dry air dryers only; drying times and temperatures may differ depending on the dryer type.

Processors are solely responsible for validating and optimizing processing parameters for their specific equipment and applications. To the maximum extent permitted by law, Covestro disclaims all liability for performance outcomes or damages resulting from reliance on these recommended conditions.

Contact Information

Please use our [contact form](#) or contact us directly by sending an e-mail to technical-datasheets@cx.covestro.com.
