

NORYL™ RESIN N802

REGION AMERICAS

DESCRIPTION

PPE/PS 80oC V2 FR high flow

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	35	MPa	SABIC - Japan Method
Tensile Strain, break	50	%	SABIC - Japan Method
Flexural Stress	53	MPa	ASTM D 790
Flexural Modulus	2150	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	78	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	80	°C	ASTM D 648
CTE, -30°C to 30°C	0.00007 – 0.00007	1/°C	TMA
PHYSICAL			
Specific Gravity	1.08	-	ASTM D 792
Water Absorption, 24 hours	0.07	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	21	g/10 min	ASTM D 1238
FLAME CHARACTERISTICS			
UL Recognized, 94V-2 Flame Class Rating	1.4	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80 – 85	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Melt Temperature	230	°C	
Nozzle Temperature	190 – 230	°C	
Front - Zone 3 Temperature	190 – 230	°C	
Middle - Zone 2 Temperature	190 – 230	°C	
Rear - Zone 1 Temperature	175 – 225	°C	
Mold Temperature	40 – 65	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	
Vent Depth	0.038 – 0.051	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.