

CYCOLACTM RESIN INP338T

REGION AMERICAS

DESCRIPTION

ABS, powder, highest impact. FDA compliant (part use must be at room temperature or below).

TYPICAL PROPERTY VALUES

Revision 20181012

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--------------------------|----------------|-------------------|--------------|
| MECHANICAL | | | |
| Hardness, Shore D | 40 | - | ASTM D 2240 |
| PHYSICAL | | | |
| Specific Gravity | 0.95 | - | ASTM D 792 |
| Density (Molded) | 0.96 | g/cm ³ | ISO 1183 |
| Mean Resin Particle Size | 200 | micrometer | SABIC method |
| Total NA Volatiles | 0.2 | % | SABIC method |
| BD | 70 | % | SABIC method |
| Bulk Density | 0.25 | g/cm ³ | ASTM D 1895 |

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.