

# NORYL<sup>TM</sup> RESIN GFN1F

REGION ASIA

## DESCRIPTION

PPE+PS blend. 10% Glass reinforced. NSF 61 listing in several colors (restrictions apply). FDA compliance (restrictions apply). Low water absorption. Hydrolytic stability. Dimensional stability. Suitable for fluid engineering applications including water filter and water meter components.

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	75	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	75	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3.5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	3.5	%	ASTM D 638
Tensile Modulus, 5 mm/min	4400	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	105	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3400	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.5	%	ISO 527
Tensile Strain, break, 50 mm/min	4.5	%	ISO 527
Tensile Modulus, 1 mm/min	3900	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	115	MPa	ISO 178
Flexural Modulus, 2 mm/min	3700	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	410	J/m	ASTM D 4812
Izod Impact, notched, 23°C	84	J/m	ASTM D 256
Izod Impact, notched, -30°C	80	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	20	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	30	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	138	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	135	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	130	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.2E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.5E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	129	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.17	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.55 – 0.66	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	4	g/10 min	ASTM D 1238
Density	1.17	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	4	cm <sup>3</sup> /10 min	ISO 1133
<b>INJECTION MOLDING</b>			
Drying Temperature	105 – 110	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	295 – 315	°C	
Front - Zone 3 Temperature	280 – 315	°C	
Middle - Zone 2 Temperature	270 – 310	°C	
Rear - Zone 1 Temperature	260 – 305	°C	
Mold Temperature	75 – 105	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.