

NORYL GTX™ RESIN NX003 1

REGION AMERICAS

DESCRIPTION

NORYL GTX NX0031 resin is a conductive resin specially designed for electrostatic painting and powder coating applications. This material combines high impact, good flow and conductivity. The material is only available in black and is suitable for injection molding.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	52	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	48	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	34	%	ASTM D 638
Tensile Modulus, 5 mm/min	2250	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	79	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2100	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	48	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	30	%	ISO 527
Tensile Modulus, 1 mm/min	2000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	1900	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	224	J/m	ASTM D 256
Izod Impact, notched, -30°C	117	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	42	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	18	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	175	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	176	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	136	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.E-04	1/°C	ASTM E 831
CTE, 23°C to 60°C, flow	1.E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	9.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	175	°C	ISO 306
Vicat Softening Temp, Rate B/120	180	°C	ISO 306
PHYSICAL			
Specific Gravity	1.09	-	ASTM D 792

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 3.2 mm	1.3 – 1.6	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	8	g/10 min	ASTM D 1238
Density	1.09	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	4.2	%	ISO 62
Moisture Absorption (23°C / 50% RH)	1.2	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	8	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.07	%	
Minimum Moisture Content	0.02	%	
Melt Temperature	270 – 295	°C	
Nozzle Temperature	270 – 295	°C	
Front - Zone 3 Temperature	265 – 295	°C	
Middle - Zone 2 Temperature	260 – 295	°C	
Rear - Zone 1 Temperature	255 – 295	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.