

FLEX NORYL™ RESIN WCV072

REGION ASIA

DESCRIPTION

Flexible, halogen free mPPE extrusion grade material for applications such as automotive wire insulation. Low specific gravity with good flame retardant and very good scrape abrasion resistance. Designed for evaluation in applications requiring ISO6722. 72 Shore D hardness. Processed using standard extrusion equipment.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	43	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	41	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	15	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	83	%	ASTM D 638
Tensile Modulus, 50 mm/min	1710	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	53	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	1550	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	44	MPa	ISO 527
Tensile Stress, break, 50 mm/min	42	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	11	%	ISO 527
Tensile Strain, break, 50 mm/min	46	%	ISO 527
Tensile Modulus, 1 mm/min	1750	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	59	MPa	ISO 178
Flexural Modulus, 2 mm/min	1740	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	309	J/m	ASTM D 256
Izod Impact, notched, -30°C	67	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	45	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	36	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	33	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	114	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	92	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.05E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.4E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.11E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	114	°C	ISO 306
Vicat Softening Temp, Rate B/120	117	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	98	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.03	-	ASTM D 792
Melt Flow Rate, 280°C/5.0 kgf	13.8	g/10 min	ASTM D 1238

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Density	1.03	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	13	cm ³ /10 min	ISO 1133
WIRE COATING EXTRUSION			
Drying Temperature	60 – 80	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Extruder Length/Diameter Ratio (L/D)	22:1 to 26:1	-	
Screw Speed	15 – 40	rpm	
Feed Zone Temperature	210 – 260	°C	
Middle Zone Temperatures	230 – 285	°C	
Head Zone Temperature	250 – 285	°C	
Neck Temperature	250 – 285	°C	
Cross-head Temperature	250 – 285	°C	
Die Temperature	250 – 285	°C	
Melt Temperature	250 – 285	°C	
Conductor Pre-heat Temperature	80 – 150	°C	
Screen Pack	150 – 100	-	
Cooling Water Air Gap	100 – 200	mm	
Water Bath Temperature	15 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.