

NORYL™ RESIN EM6100

REGION AMERICAS

DESCRIPTION

PPE+PS blend. Unfilled. Good balance of flow/heat/impact. Dimensional stability. Paint adhesion. Suitable for the automotive interior market: HVAC housings, radio components. MS-DB424, WSB-M4D844-A9, GMP.PPE.007.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	40	MPa	ASTM D 638
Tensile Stress, yld, Type I, 50 mm/min	43	MPa	ASTM D 638
Tensile Strain, yield	3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	65	%	ASTM D 638
Tensile Modulus, 5 mm/min	1900	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	67	MPa	ASTM D 790
Flexural Stress, yld, 2.6 mm/min, 100 mm span	66	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2100	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2000	MPa	ASTM D 790
Tensile Stress, yield	42	MPa	ISO 527
Tensile Stress, break	40	MPa	ISO 527
Tensile Strain, yield	2.8	%	ISO 527
Tensile Strain, break	60	%	ISO 527
Tensile Modulus, 1 mm/min	2050	MPa	ISO 527
Flexural Stress	65	MPa	ISO 178
Flexural Modulus	2100	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	453	J/m	ASTM D 256
Izod Impact, notched, -30°C	250	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	36	J	ASTM D 3763
Instrumented Impact Energy @ peak, -30	24	J	ASTM D 3763
Instrumented Impact Total Energy, 23°C	42	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	33	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	15	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	33	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	19	kJ/m ²	ISO 179/2C
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	124	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	106	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	115	°C	ASTM D 648
CTE, 0°C to 100°C, flow	1.17E-04	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/50	119	°C	ISO 306
Vicat Softening Temp, Rate B/120	123	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	126	°C	ISO 75/Bf

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	110	°C	ISO 75 /Af
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL			
Specific Gravity	1.05	-	ASTM D 792
Water Absorption, 24 hours	0.2	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	15	g/ 10 min	ASTM D 1238
Melt Volume Rate, MVR at 280°C/5.0 kg	15	cm ³ / 10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.49	mm	UL 94
INJECTION MOLDING			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	265 – 295	°C	
Nozzle Temperature	265 – 295	°C	
Front - Zone 3 Temperature	255 – 295	°C	
Middle - Zone 2 Temperature	245 – 290	°C	
Rear - Zone 1 Temperature	230 – 280	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	
Vent Depth	0.038 – 0.051	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.