

# FLEX NORYL™ RESIN WCD915

REGION ASIA

## DESCRIPTION

Flexible and non-halogenated flame retardant extrusion grade intended for evaluation in applications such as insulation materials. Flame retardant performance capable of meeting UL 1581 VW-1 requirement. 90C or 105C temperature rating as defined by UL 62 TPE category. 91 Shore A hardness. Processing typically conducted on standard extrusion equipment. UL 1581 tests conducted on 2.0 mm wire with 0.12 mm x 20 stranded copper conductor.

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, brk, Type I, 50 mm/min	15	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	170	%	ASTM D 638
Flexural Modulus, 12.5 mm/min, 100 mm span	100	MPa	ASTM D 790
Hardness, Shore A, 30S reading	91	-	ASTM D 2240
Tensile Stress, break, 50 mm/min	14	MPa	ISO 527
Tensile Strain, break, 50 mm/min	155	%	ISO 527
Flexural Modulus, 12.5 mm/min	70	MPa	ISO 178
<b>IMPACT</b>			
Brittleness Temperature	<-40	°C	ASTM D 746
<b>PHYSICAL</b>			
Specific Gravity	1.03	-	ASTM D 792
Melt Flow Rate, 250°C/10.0 kgf	9	g/10 min	ASTM D 1238
<b>ELECTRICAL</b>			
Volume Resistivity	3.3E+16	Ohm-cm	ASTM D 257
Relative Permittivity, 1 MHz	2.6	-	ASTM D 150
Dissipation Factor, 1 MHz	0.033	-	ASTM D 150
Dielectric strength in oil, 2.0mm	22	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
<b>FLAME CHARACTERISTICS</b>			
Smoke Density on 0.5mm plaque, Non-flame, Ds, max	49	-	ASTM E 662
Smoke Density on 0.5mm plaque, Flame, Ds, max	115	-	ASTM E 662
Glow Wire Flammability Index 960°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	825	°C	IEC 60695-2-13
Oxygen Index (LOI)	28	%	ISO 4589
<b>WIRE AND CABLE - UL 1581 TESTED ON 2.0MM WIRE WITH 0.12MMX20 STRANDED COPPER</b>			
Tensile strength @ break	24	MPa	UL 1581
Tensile elongation @ break	265	%	UL 1581
Tensile strength @ break after 7days @136°C	23	MPa	UL 1581
Tensile elongation @ break after 7days @136°C	230	%	UL 1581
Heat Deformation at 121°C/250g	5	%	UL 1581
VW-1	Pass	-	UL 1581
<b>WIRE COATING EXTRUSION</b>			
Drying Temperature	75 – 85	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	5 – 7	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Extruder Length/Diameter Ratio (L/D)	22:1 to 26:1	-	
Screw Speed	15 – 85	rpm	
Feed Zone Temperature	180 – 220	°C	
Middle Zone Temperatures	220 – 250	°C	
Head Zone Temperature	220 – 250	°C	
Neck Temperature	220 – 250	°C	
Cross-head Temperature	220 – 250	°C	
Die Temperature	220 – 250	°C	
Melt Temperature	220 – 250	°C	
Conductor Pre-heat Temperature	25 – 120	°C	
Screen Pack	150 – 100	-	
Cooling Water Air Gap	100 – 200	mm	
Water Bath Temperature	15 – 60	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.