

CYCOLOY™ FR RESIN CX7720

REGION ASIA

DESCRIPTION

CYCOLOY CX7720 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) blend is an injection moldable, high flow, high heat resistant, non chlorinated/brominated flame retardant grade. It has a UL94 V0@1.2mm, 5VA@2.5mm and 5VB@1.5mm flame rating. This grade has improved chemical resistance compared to standard PC/ABS blends and is a good candidate for thin wall applications.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	66	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	126	%	ASTM D 638
Tensile Modulus, 50 mm/min	2860	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	99	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2810	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	65	MPa	ISO 527
Tensile Stress, break, 50 mm/min	65	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	122	%	ISO 527
Tensile Modulus, 1 mm/min	2900	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	97	MPa	ISO 178
Flexural Modulus, 2 mm/min	2090	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	150	J/m	ASTM D 256
Izod Impact, notched, -30°C	63	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	62	J	ASTM D 3763
Izod Impact, notched 80°10°3 +23°C	11	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°3 -30°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 +23°C	8	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°3 sp=62mm	11	kJ/m ²	ISO 179/1eA
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	11	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	127	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	122	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	110	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	124	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	115	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.06E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.59E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.06E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.59E-05	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	127	°C	ISO 306
Vicat Softening Temp, Rate B/120	129	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	110	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	9	g/10 min	ASTM D 1238
Melt Flow Rate, 260°C/5.0 kgf	25	g/10 min	ASTM D 1238
Density	1.22	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.15	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 260°C/5.0 kg	22	cm ³ /10 min	ISO 1133
ELECTRICAL			
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94V-1 Flame Class Rating	1	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	1.2	mm	UL 94
UL Recognized, 94-5VA Rating	2.5	mm	UL 94
UL Recognized, 94-5VB Rating	1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	270 – 300	°C	
Nozzle Temperature	265 – 300	°C	
Front - Zone 3 Temperature	265 – 300	°C	
Middle - Zone 2 Temperature	260 – 300	°C	
Rear - Zone 1 Temperature	260 – 300	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.