

SABIC[®] PP RELY 71EK71PS

PP IMPACT COPOLYMER

DESCRIPTION

This impact copolymer has a high molecular weight and is provided with a long-term heat stabilisation package. It exhibits high stiffness in combination with very high impact strength even at low temperatures. This material is typically used for extrusion of sewage pipe applications and can also be typically used for blow-moulding of large containers and sheet extrusion.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>

This grade material is UL registered under File E111275 (www.ul.com)
IMDS 80775790

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	0.30	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
FORMULATION			
Anti static agent	<input type="checkbox"/>	-	-
Nucleating agent	<input checked="" type="checkbox"/>	-	-
MECHANICAL PROPERTIES			
Tensile test			
stress at yield	28	MPa	ISO 527-2 1A
tensile modulus ⁽¹⁾	1450	MPa	ISO 527-2 1A
strain at yield ⁽²⁾	8	%	ISO 527-2 1A
Izod impact notched			
at 0 °C	35	kJ/m ²	ISO 180/1A
at -20 °C	6	kJ/m ²	ISO 180/1A
Izod impact notched			
at 23 °C	No Break	kJ/m ²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	80	kJ/m ²	ISO 179/1eA
at 0 °C	20	kJ/m ²	ISO 179/1eA
at -20 °C	7	kJ/m ²	ISO 179/1eA
Charpy impact unnotched			
at 23 °C	No Break	kJ/m ²	ISO 179/1eU
Hardness Shore D	66	-	ISO 868
THERMAL PROPERTIES			
Heat deflection temperature ⁽³⁾			
at 0.45 MPa (HDT/B)	95	°C	ISO 75
at 1.80 MPa (HDT/A)	55	°C	ISO 75
Vicat Softening Temperature ⁽⁴⁾			
at 10 N (VST/A)	156	°C	ISO 306

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
at 50 N (VST/B)	81	°C	ISO 306
OIT 200°C	>100	min	EN 728

- (1) Speed of testing: 1 mm/min
- (2) Speed of testing: 50 mm/min
- (3) Flat wise (testbar 80*10*4mm)
- (4) Temperature rate: 120°C/h

QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.