

CYCOLOY™ FR RESINS C2950

REGION ASIA

DESCRIPTION

CYCOLOY C2950 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) resin is a standard high heat grade that can be injection molded. This non-chlorinated, non-brominated flame retardant high heat PC/ABS has a UL V0 & 5VB flame rating. CYCOLOY C2950 resin is an excellent candidate for a wide variety of applications including appliances, lighting and electrical.

TYPICAL PROPERTY VALUES

Revision 20191022

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	40	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	102	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2650	MPa	ASTM D 790
Hardness, Rockwell R	123	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	534	J/m	ASTM D 256
Izod Impact, notched, -30°C	160	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	61	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	54	J	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	112	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	90	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	104	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	95	°C	ASTM D 648
CTE, -30°C to 30°C, flow	7.2E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.2E-05	1/°C	ASTM D 696
Thermal Conductivity	0.2	W/m-°C	ASTM C177
Relative Temp Index, Elec	85	°C	UL 746B
Relative Temp Index, Mech w/impact	85	°C	UL 746B
Relative Temp Index, Mech w/o impact	85	°C	UL 746B
PHYSICAL			
Specific Gravity	1.18	-	ASTM D 792
Specific Gravity, color	1.22	-	ASTM D 792
Water Absorption, 24 hours	0.1	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.4	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	10	g/10 min	ASTM D 1238
ELECTRICAL			
Volume Resistivity	1.E+17	Ohm-cm	ASTM D 257
Surface Resistivity	>1.E+16	Ohm	ASTM D 257
Dielectric Strength, in oil, 3.2 mm	19.4	kV/mm	ASTM D 149

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Permittivity, 50/60 Hz	3	-	ASTM D 150
Relative Permittivity, 100 Hz	3	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.005	-	ASTM D 150
Dissipation Factor, 100 Hz	0.0049	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E207780-228471	-	-
UL Yellow Card Link 2	E45587-236935	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	2.49	mm	UL 94
Oxygen Index (LOI)	32	%	ASTM D 2863
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	245 – 275	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	245 – 275	°C	
Middle - Zone 2 Temperature	220 – 275	°C	
Rear - Zone 1 Temperature	220 – 255	°C	
Mold Temperature	60 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.