

LNPT[™] FARADEx[™] COMPOUND MS003

MS-1003
REGION ASIA

DESCRIPTION

LNPT[™] FARADEx[™] MS003 is a compound based on Polypropylene resin containing 15% Stainless Steel. Added features of this material include: Electrically Conductive, EMI/RFI Shielding.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	19	MPa	ASTM D 638
Tensile Stress, break	15	MPa	ASTM D 638
Tensile Strain, yield	6.2	%	ASTM D 638
Tensile Strain, break	88.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	1190	MPa	ASTM D 638
Flexural Stress	27	MPa	ASTM D 790
Flexural Modulus	1190	MPa	ASTM D 790
Tensile Stress, yield	21	MPa	ISO 527
Tensile Stress, break	15	MPa	ISO 527
Tensile Strain, yield	5.2	%	ISO 527
Tensile Strain, break	72	%	ISO 527
Tensile Modulus, 1 mm/min	1300	MPa	ISO 527
Flexural Stress	32	MPa	ISO 178
Flexural Modulus	1500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	1226	J/m	ASTM D 4812
Izod Impact, notched, 23°C	267	J/m	ASTM D 256
Multiaxial Impact	22	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	80	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	92	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	53	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.04E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.72E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	1.43E-04	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.7E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	95	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	56	°C	ISO 75/Af
PHYSICAL			
Density	1.01	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	120	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	130	%	ASTM D 955

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 24 hrs	1.2	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	1.3	%	ISO 294
Density	1.01	g/cm ³	ISO 1183
ELECTRICAL			
Volume Resistivity	1.E+04	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+03	Ohm	ASTM D 257
Shielding Effectivness @ 3mm	50 – 65	dB	SABIC method
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Melt Temperature	230 – 250	°C	
Front - Zone 3 Temperature	260 – 270	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Rear - Zone 1 Temperature	205 – 215	°C	
Mold Temperature	30 – 55	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	25 – 50	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.