

VALOX™ RESIN EH7020HF

REGION ASIA

DESCRIPTION

VALOX EH7020HF is a mineral filled PBT/PET that offers good surface appearance, high flow and good heat performance. EH7020HF was developed for automotive bezel application that requires basecoat + top coat metalization. EH7020HF is higher flow version of EH7020.

TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	56	MPa	SABIC - Japan Method
Tensile Stress, yld, Type I, 5 mm/min	55	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	55	MPa	ASTM D 638
Tensile Strain, break	8	%	SABIC - Japan Method
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	5880	MPa	ASTM D 638
Flexural Stress, yield, 6.4 mm	96	MPa	ASTM D 790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	4680	MPa	ASTM D 790
Flexural Modulus, 6.4 mm	4860	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	45	MPa	ISO 527
Tensile Stress, break, 5 mm/min	57	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.5	%	ISO 527
Tensile Strain, break, 5 mm/min	1.9	%	ISO 527
Tensile Modulus, 1 mm/min	4800	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	96	MPa	ISO 178
Flexural Modulus, 2 mm/min	4710	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	31	J/m	ASTM D 256
Izod Impact, notched, -30°C	31	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	4	J	ASTM D 3763
Izod Impact, notched 80°10°4 +23°C	2	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	2	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	2	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	180	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	70	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	200	°C	ASTM D 648
CTE, -40°C to 40°C, flow	5.29E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.2E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	5.29E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.2E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	75	-	IEC 60695-10-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	180	°C	ISO 306
Vicat Softening Temp, Rate B/120	179	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	77	°C	ISO 75/Ae
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	89	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.49	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow	1.53 – 1.57	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	1.037 – 1.059	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	1.147 – 1.18	%	SABIC method
Melt Flow Rate, 265°C/2.16kgf	64	g/10 min	ASTM D 1238
Melt Flow Rate, 266°C/1.2 kgf	36	g/10 min	ASTM D 1238
Density	1.49	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.42	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.42	%	ISO 62
Melt Volume Rate, MVR at 265°C/2.16 kg	52	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.