

# CYCOLACT™ RESIN GX3800F

REGION ASIA

## DESCRIPTION

High impact ABS for sheet extrusion. FDA food contact compliant.

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	39	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	30	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3.1	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	31.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	2080	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	66	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2160	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	432	J/m	ASTM D 256
Izod Impact, notched, -30°C	299	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	50	J	ASTM D 3763
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	106	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	93	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.01E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.04E-04	1/°C	ASTM E 831
<b>PHYSICAL</b>			
Specific Gravity	1.03	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.8	%	SABIC method
Melt Viscosity, 240°C, 100 sec-1	14000	Poise	ASTM D 3825
Melt Volume Rate, MVR at 220°C/10.0 kg	4	cm <sup>3</sup> /10 min	ISO 1133
<b>EXTRUSION BLOW MOLDING</b>			
Drying Temperature	80 – 90	°C	
Drying Time	4 – 5	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature (Parison)	215 – 230	°C	
Barrel - Zone 1 Temperature	205 – 225	°C	
Barrel - Zone 2 Temperature	205 – 225	°C	
Barrel - Zone 3 Temperature	205 – 225	°C	
Barrel - Zone 4 Temperature	205 – 225	°C	
Adapter - Zone 5 Temperature	210 – 230	°C	
Head - Zone 6 - Top Temperature	215 – 230	°C	
Head - Zone 7 - Bottom Temperature	215 – 230	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	20 – 60	rpm	
Extruder Feed Zone Temperature	60 – 75	°C	
Mold Temperature	40 – 80	°C	
Die Temperature	215 – 235	°C	
<b>SHEET EXTRUSION</b>			
Drying Temperature	80 – 95	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	215 – 260	°C	
Barrel - Zone 1 Temperature	170 – 200	°C	
Barrel - Zone 2 Temperature	180 – 220	°C	
Barrel - Zone 3 Temperature	190 – 225	°C	
Barrel - Zone 4 Temperature	200 – 240	°C	
Adapter Temperature	205 – 250	°C	
Die Temperature	205 – 250	°C	
Roll Stack Temp - Top	90 – 95	°C	
Roll Stack Temp - Middle	95 – 105	°C	
Roll Stack Temp - Bottom	100 – 105	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.