

CYCOLACT™ RESIN DL100

REGION ASIA

DESCRIPTION

CYCOLAC DL100 is a high heat, high impact, low emissions ABS/PC blend.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	44	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	90	%	ASTM D 638
Tensile Modulus, 5 mm/min	2240	MPa	ASTM D 638
Hardness, Rockwell R	104	-	ASTM D 785
Tensile Stress, yield, 5 mm/min	46	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.5	%	ISO 527
Tensile Strain, break, 5 mm/min	60	%	ISO 527
Tensile Strain, yield, 50 mm/min	3.4	%	ISO 527
Tensile Strain, break, 50 mm/min	10	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	69	MPa	ISO 178
Flexural Modulus, 2 mm/min	2250	MPa	ISO 178
Hardness, H358/30	91	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	700	J/m	ASTM D 256
Izod Impact, notched, 23°C, 6.4mm	550	J/m	ASTM D 256
Izod Impact, notched 80°10°4 +23°C	35	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	15	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	34	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10°4 sp=62mm	14	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	105	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	88	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	90	°C	ASTM D 648
CTE, 23°C to 60°C, flow	9.8E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	9.8E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	105	°C	ISO 306
Vicat Softening Temp, Rate B/120	107	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120°10°4 sp=100mm	104	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120°10°4 sp=100mm	87	°C	ISO 75/Ae
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Density	1.08	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	7	g/10 min	ISO 1133
Melt Volume Rate, MVR at 260°C/5.0 kg	8	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94HB Flame Class Rating 2nd value	3	mm	UL 94
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	250 – 280	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	250 – 280	°C	
Middle - Zone 2 Temperature	250 – 280	°C	
Rear - Zone 1 Temperature	230 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	40 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.