

# VALOX™ RESIN VIC43 1 1

REGION ASIA

## DESCRIPTION

VALOX VIC43 1 1 is a 30% glass filled, impact modified PBT with excellent epoxy adhesion. Automotive underhood applications such as ignition coil housings.

## TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield	96	MPa	SABIC - Japan Method
Tensile Strain, break	5 – 5	%	SABIC - Japan Method
Flexural Stress	128	MPa	ASTM D 790
Flexural Modulus	6080	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	137	J/m	ASTM D 256
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	220	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	205	°C	ASTM D 648
CTE, -30°C to 30°C	0.00003 – 0.00003	1/°C	TMA
<b>PHYSICAL</b>			
Specific Gravity	1.43	-	ASTM D 792
Water Absorption, 24 hours	0.07	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.4	%	SABIC method
Mold Shrinkage, flow, 6.4 mm	0.6 – 0.8	%	SABIC method
<b>ELECTRICAL</b>			
Surface Resistivity	1.E+16	Ohm	ASTM D 257
Relative Permittivity, 50/60 Hz	3	-	ASTM D 150

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.