

NORYLTM RESIN ENG265F

REGION AMERICAS

DESCRIPTION

PPE+PS blend. Unfilled. Suitable for profile extrusion. NSF listed for potable water use in several colors (Standard 61). Low water absorption. Hydrolytic stability. Dimensional stability. Typical applications include tubes for reverse osmosis systems.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	50	MPa	ASTM D 638
Tensile Stress, yld, Type I, 50 mm/min	56	MPa	ASTM D 638
Tensile Strain, yield	3.3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	28	%	ASTM D 638
Tensile Modulus, 5 mm/min	2400	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	89	MPa	ASTM D 790
Flexural Stress, yld, 2.6 mm/min, 100 mm span	88	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2550	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2450	MPa	ASTM D 790
Hardness, Rockwell R	119	-	ASTM D 785
Tensile Stress, yield	55	MPa	ISO 527
Tensile Stress, break	50	MPa	ISO 527
Tensile Strain, yield	3.1	%	ISO 527
Tensile Strain, break	27	%	ISO 527
Tensile Modulus, 1 mm/min	2550	MPa	ISO 527
Flexural Stress	95	MPa	ISO 178
Flexural Modulus	2500	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	186	J/m	ASTM D 256
Izod Impact, notched, -30°C	114	J/m	ASTM D 256
Gardner, -30°C	25	J	ASTM D 3029
Gardner, -40°C	5	J	ASTM D 3029
Instrumented Impact Total Energy, 23°C	39	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	13	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	10	kJ/m ²	ISO 179/2C
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	132	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	118	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	126	°C	ASTM D 648
CTE, -40°C to 95°C, flow	5.94E-05	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/50	137	°C	ISO 306

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/120	141	°C	ISO 306
Relative Temp Index, Elec	105	°C	UL 746B
Relative Temp Index, Mech w/impact	90	°C	UL 746B
Relative Temp Index, Mech w/o impact	105	°C	UL 746B
PHYSICAL			
Specific Gravity	1.06	-	ASTM D 792
Water Absorption, 24 hours	0.06	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	8.5	g/10 min	ASTM D 1238
Melt Volume Rate, MVR at 280°C/5.0 kg	8	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	19.7	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	2.65	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0004	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
EXTRUSION			
Drying Temperature	105 – 115	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	-	%	
Melt Temperature	225 – 255	°C	
Barrel - Zone 1 Temperature	205	°C	
Barrel - Zone 2 Temperature	205	°C	
Barrel - Zone 3 Temperature	225	°C	
Barrel - Zone 4 Temperature	225	°C	
Adapter Temperature	250	°C	
Die Temperature	250	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.