

# XENOY™ RESIN 1105

REGION ASIA

## DESCRIPTION

PBT/PC blend, injection molding grade, non-reinforced, impact modified, excellent toughness at low temperatures, very good paintability

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	48	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	47	MPa	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	45	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	46	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.2	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	120	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.1	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	110	%	ASTM D 638
Tensile Modulus, 50 mm/min	2010	MPa	ASTM D 638
Tensile Modulus, 5 mm/min	1980	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	76	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	74	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	1900	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	52	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.5	%	ISO 527
Tensile Strain, break, 50 mm/min	116	%	ISO 527
Tensile Modulus, 1 mm/min	2070	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	78	MPa	ISO 178
Flexural Strain, break, 2 mm/min	7.3	%	ISO 178
Flexural Modulus, 2 mm/min	2010	MPa	ISO 178
Hardness, Shore D	79	-	ISO 868
<b>IMPACT</b>			
Izod Impact, notched, 23°C	755	J/m	ASTM D 256
Izod Impact, notched, 0°C	715	J/m	ASTM D 256
Izod Impact, notched, -10°C	695	J/m	ASTM D 256
Izod Impact, notched, -20°C	687	J/m	ASTM D 256
Izod Impact, notched, -30°C	489	J/m	ASTM D 256
Izod Impact, notched, -40°C	372	J/m	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	63	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	51	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -40°C	34	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	62	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	47	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	122	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	115	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	97	°C	ASTM D 648
Vicat Softening Temp, Rate B/50	122	°C	ISO 306
Vicat Softening Temp, Rate B/120	123	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	109	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	90	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.2	-	ASTM D 792
Specific Volume	1.2	cm <sup>3</sup> /g	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.8 – 1	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.8 – 1	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	16	g/10 min	ASTM D 1238
Density	1.2	g/cm <sup>3</sup>	ISO 1183
Melt Flow Rate, 250°C/5.0 kg	16	g/10 min	ISO 1133
<b>INJECTION MOLDING</b>			
Drying Temperature	110	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 275	°C	
Nozzle Temperature	255 – 270	°C	
Front - Zone 3 Temperature	255 – 275	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	245 – 265	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.