

ULTEM™ RESIN CRS5111

REGION ASIA

DESCRIPTION

10% Glass fiber filled, enhanced flow Polyetherimide copolymer (Tg 225C) with enhanced chemical resistance to strong acids, bases, aromatics, and ketones. ECO conforming, UL94 V0 and 5 VA listing.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	117	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	112	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Modulus, 5 mm/min	4750	MPa	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	193	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	4890	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	37	J/m	ASTM D 256
Izod Impact, Reverse Notched, 3.2 mm	357	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	215	°C	ASTM D 648
Relative Temp Index, Elec	105	°C	UL 746B
Relative Temp Index, Mech w/impact	105	°C	UL 746B
Relative Temp Index, Mech w/o impact	105	°C	UL 746B
PHYSICAL			
Specific Gravity	1.36	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.7 – 0.9	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	6.9	g/10 min	ASTM D 1238
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	1.47	mm	UL 94
UL Recognized, 94-5VA Rating	1.47	mm	UL 94
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	365 – 390	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Nozzle Temperature	360 – 380	°C	
Front - Zone 3 Temperature	365 – 390	°C	
Middle - Zone 2 Temperature	355 – 375	°C	
Rear - Zone 1 Temperature	345 – 365	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.