

# XENOY™ RESIN 6370

REGION ASIA

## DESCRIPTION

30% glass-reinforced, impact modified thermoplastic alloy. Improved toughness and ductility.

## TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	97	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	91	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Modulus, 5 mm/min	9750	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	150	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	138	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	5370	MPa	ASTM D 790
Hardness, Rockwell R	109	-	ASTM D 785
Tensile Stress, yield, 5 mm/min	105	MPa	ISO 527
Tensile Stress, break, 5 mm/min	105	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	8500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	154	MPa	ISO 178
Flexural Modulus, 2 mm/min	7750	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	640	J/m	ASTM D 4812
Izod Impact, notched, 23°C	170	J/m	ASTM D 256
Izod Impact, notched, -30°C	112	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	5	J	ASTM D 3763
Instrumented Impact Total Energy, 23°C	17	J	ASTM D 3763
Izod Impact, notched 80°10'4 +23°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	9	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	153	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	163	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	204	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	149	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.7E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.1E-04	1/°C	ASTM E 831
CTE, 60°C to 138°C, flow	1.98E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.7E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.1E-04	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	148	°C	ISO 306
Vicat Softening Temp, Rate B/120	150	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	155	°C	ISO 75/Af
Relative Temp Index, Elec	140	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.44	-	ASTM D 792
Specific Volume	0.7	cm <sup>3</sup> /g	ASTM D 792
Water Absorption, 24 hours	0.09	%	ASTM D 570
Mold Shrinkage, flow, 0.75-2.3 mm	0.3 – 0.4	%	SABIC method
Mold Shrinkage, flow, 2.3-4.6 mm	0.4 – 0.5	%	SABIC method
Mold Shrinkage, xflow, 0.75-2.3 mm	0.4 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 2.3-4.6 mm	0.7 – 0.9	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	24	g/10 min	ASTM D 1238
Density	1.44	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.5	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	12	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	19	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL</b>			
Volume Resistivity	4.8E+15	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	20	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	27	kV/mm	ASTM D 149
Relative Permittivity, 100 Hz	4	-	ASTM D 150
Relative Permittivity, 1 MHz	4	-	ASTM D 150
Dissipation Factor, 100 Hz	0.003	-	ASTM D 150
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	3	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
<b>INJECTION MOLDING</b>			
Drying Temperature	110	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 280	°C	
Nozzle Temperature	255 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	255 – 275	°C	
Rear - Zone 1 Temperature	250 – 270	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	65 – 95	°C	
Back Pressure	0.3 – 0.6	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.