

LNP™ THERMOCOMP™ COMPOUND DX11355

REGION ASIA

DESCRIPTION

This is a PC based compound with good plating, surface, mechanical performance and flame retardant (Halogen free), a good candidate for Laser Direct Structuring applications.

TYPICAL PROPERTY VALUES

Revision 20180517

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	52	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	70	%	ASTM D 638
Tensile Modulus, 50 mm/min	2600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	90	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	89	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	800	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	114	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.2E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.7E-05	1/°C	ASTM E 831
PHYSICAL			
Density	1.27	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.01	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.5	%	ASTM D 955
Melt Flow Rate, 300°C/1.2 kgf	12	g/10 min	ASTM D 1238
ELECTRICAL			
Relative Permittivity, 1 GHz	2.92	-	IEC 60250
Dissipation Factor, 1 GHz	0.007	-	IEC 60250
FLAME CHARACTERISTICS			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Recognized, 94V-0 Flame Class Rating (3)	0.6	mm	UL 94
INJECTION MOLDING			
Drying Temperature	100 – 110	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	275 – 300	°C	
Nozzle Temperature	275 – 300	°C	
Front - Zone 3 Temperature	260 – 300	°C	
Middle - Zone 2 Temperature	255 – 295	°C	
Rear - Zone 1 Temperature	250 – 290	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.