



PP LGF REINFORCED REGION EUROPE

DESCRIPTION

SABIC[®] STAMAX 40YM241 is a high heat resistant 40% long glass fiber reinforced grade. The glass fibers are chemically coupled to the PP matrix, resulting in high stiffness and strength.

IMDS ID: 459463868

TYPICAL PROPERTY VALUES

PROPERTIES **TYPICAL VALUES** UNITS **TEST METHODS** POLYMER PROPERTIES 1220 150 1183 Density kg/m³ 40 ISO 3451 Glass fibre content % MECHANICAL PROPERTIES (1) Tensile modulus 8200 ISO 527/1A at 23 °C MPa at 80 °C 5400 MPa ISO 527/1A Tensile strength at 23 °C 110 ISO 527/1A MPa at 80 °C 65 MPa ISO 527/1A Tensile elongation at break 2.1 ISO 527/1A at 23 °C % Flexural Modulus at 23 °C 8700 MPa ISO 178 at 80 °C 6100 MPa ISO 178 Flexural strength at 23 °C 180 MPa ISO 178 at 80 °C ISO 178 105 MPa Charpy Impact Strength Notched at 23 °C 26 kJ/m² ISO 179/1eA at -30 °C 25 kJ/m² ISO 179/1eA Charpy impact unnotched at 23 °C 55 kJ/m² ISO 179/1eU at -30 °C 50 kJ/m² ISO 179/1eU THERMAL PROPERTIES Heat deflection temperature °C at 1.80 MPa (HDT/A) 158 ISO 75/A Coeff. of linear thermal expansion -30 °C to 100 °C 40 µm/mK ISO 11359-2

(1) All measurements on injection molded samples.

© 2019 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS

Revision 20190213



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.