

# LEXAN™ FR RESIN BFL2015

REGION ASIA

## DESCRIPTION

Non-brominated, non-chlorinated flame retardant, glass reinforced PC. Opaque colors only

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield	81	MPa	SABIC - Japan Method
Tensile Stress, yld, Type I, 50 mm/min	92	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	91	MPa	ASTM D 638
Tensile Strain, break	4 – 6	%	SABIC - Japan Method
Tensile Strain, yld, Type I, 50 mm/min	3.5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Modulus, 5 mm/min	5330	MPa	ASTM D 638
Flexural Stress	133	MPa	ASTM D 790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	156	MPa	ASTM D 790
Flexural Modulus	4410	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	4600	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	103	MPa	ISO 527
Tensile Stress, break, 50 mm/min	100	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.6	%	ISO 527
Tensile Strain, break, 50 mm/min	4.3	%	ISO 527
Tensile Modulus, 1 mm/min	4950	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	150	MPa	ISO 178
Flexural Modulus, 2 mm/min	4280	MPa	ISO 178
<b>IMPACT</b>			
Charpy Impact, unnotched, 23°C	67	kJ/m <sup>2</sup>	ISO 179/2C
Charpy Impact, unnotched, -30°C	75	kJ/m <sup>2</sup>	ISO 179/2C
Izod Impact, notched, 23°C	78	J/m	ASTM D 256
Izod Impact, notched, -30°C	N/A	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	61	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	80	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	80	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	8	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	8	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	6	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	100	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	100	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy Impact, notched, 23°C	12	kJ/m <sup>2</sup>	ISO 179/2C
Charpy Impact, notched, -30°C	8	kJ/m <sup>2</sup>	ISO 179/2C
<b>THERMAL</b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	148	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	145	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	141	°C	ASTM D 648
CTE, -30°C to 30°C, flow	4.E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	4.E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C	0.00004 – 0.00005	1/°C	TMA
CTE, 23°C to 80°C, flow	4.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	4.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSE50	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	149	°C	ISO 306
Vicat Softening Temp, Rate B/120	150	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	132	°C	ISO 75/Af
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.23	-	ASTM D 792
Water Absorption, 24 hours	0.14	%	ASTM D 570
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.5	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.5	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.2 – 0.5	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	6.5	g/10 min	ASTM D 1238
Density	1.3	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.35	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	6	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL</b>			
Dielectric Strength, in oil, 1.6 mm	20	kV/mm	ASTM D 149
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Relative Permittivity, 1 MHz	3.1	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.02	-	IEC 60250
Dissipation Factor, 1 MHz	0.01	-	IEC 60250
Comparative Tracking Index	150	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.2	-	IEC 60250
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
Oxygen Index (LOI)	38	%	ISO 4589
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	290 – 320	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Nozzle Temperature	280 – 310	°C	
Front - Zone 3 Temperature	290 – 320	°C	
Middle - Zone 2 Temperature	280 – 310	°C	
Rear - Zone 1 Temperature	270 – 300	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 120	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.