

LEXANT™ RESIN EM3110

REGION ASIA

DESCRIPTION

Automotive interiors. Optimizes flow/processability for cost effective thinner wall design uses.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	81	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2030	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	640	J/m	ASTM D 256
Izod Impact, notched, -20°C	587	J/m	ASTM D 256
Izod Impact, notched, -30°C	213	J/m	ASTM D 256
Izod Impact, notched, 23°C, 6.4mm	213	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	56	J	ASTM D 3763
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	118	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	126	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	123	°C	ASTM D 648
CTE, -40°C to 95°C, flow	6.48E-05	1/°C	ASTM E 831
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Water Absorption, 24 hours	0.16	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	20	g/10 min	ASTM D 1238
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	10	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	275 – 300	°C	
Nozzle Temperature	270 – 295	°C	
Front - Zone 3 Temperature	275 – 300	°C	
Middle - Zone 2 Temperature	265 – 290	°C	
Rear - Zone 1 Temperature	255 – 275	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.