

CYCOLOY™ FR RESINS CY6120

REGION ASIA

DESCRIPTION

Non-chlorinated and non-brominated flame retardant PC/ABS featuring good flow and impact properties. UL-94 V0 listed at 1.2mm intended for various thin wall applications.

TYPICAL PROPERTY VALUES

Revision 20191022

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	59	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Modulus, 50 mm/min	2960	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	102	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2820	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	58	MPa	ISO 527
Tensile Stress, break, 50 mm/min	49	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	100	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	93	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	587	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	54	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/50	96	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	93	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	85	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.38E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.46E-05	1/°C	ASTM E831
CTE, 23°C to 80°C, flow	8.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	95	°C	ISO 306
Vicat Softening Temp, Rate B/120	98	°C	ISO 306
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.19	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.5	%	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Flow Rate, 260°C/2.16 kgf	18	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 260°C/2.16 kg	16	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.6	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0041	-	IEC 60250
Dissipation Factor, 1 MHz	0.0086	-	IEC 60250
Relative Permittivity, 50/60 Hz	2.7	-	IEC 60250
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	1.19	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	245 – 275	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	245 – 275	°C	
Middle - Zone 2 Temperature	220 – 265	°C	
Rear - Zone 1 Temperature	220 – 255	°C	
Mold Temperature	60 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.