

VALOX™ FR RESIN 357U

REGION ASIA

DESCRIPTION

VALOX 357U Polycarbonate/Polybutylene Terephthalate (PC/PBT) resin is a non-reinforced, impact modified, UV stabilized, injection moldable grade. This brominated flame retardant PC/PBT has a UL V0 and 5VA rating. VALOX 357U resin is a general purpose resin that is an excellent candidate for a wide variety of applications including bobbins, switches and enclosures.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Modulus, 50 mm/min	2050	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	48	MPa	ASTM D 638
Tensile Stress, yld, Type I, 50 mm/min	48	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Tensile Strain, yield, 50 mm/min	5.28	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	82	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	82	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2060	MPa	ASTM D 790
Hardness, Rockwell R	117	-	ASTM D 785
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D 4812
Izod Impact, notched, 23°C	534	J/m	ASTM D 256
Gardner, 23°C	43	J	ASTM D 3029
Modified Gardner, 23°C	43	J	ASTM D 3029
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	98	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.18E-05	1/°C	ASTM E 831
CTE, 60°C to 138°C, flow	1.24E-04	1/°C	ASTM E 831
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.34	-	ASTM D 792
Specific Volume	0.75	cm ³ /g	ASTM D 792
Water Absorption, 24 hours	0.08	%	ASTM D 570
Mold Shrinkage, flow, 0.75-2.3 mm	0.8 – 1.1	%	SABIC method
Mold Shrinkage, flow, 2.3-4.6 mm	1 – 1.4	%	SABIC method
Mold Shrinkage, xflow, 0.75-2.3 mm	0.9 – 1.3	%	SABIC method
Mold Shrinkage, xflow, 2.3-4.6 mm	1.2 – 1.6	%	SABIC method
ELECTRICAL			
Volume Resistivity	>1.2E+16	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	18.5	KV/mm	ASTM D 149

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Strength, in oil, 1.6 mm	25.2	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	18.5	kV/mm	ASTM D 149
Relative Permittivity, 100 Hz	3.2	-	ASTM D 150
Relative Permittivity, 1 MHz	3.2	-	ASTM D 150
Dissipation Factor, 100 Hz	0.003	-	ASTM D 150
Dissipation Factor, 1 MHz	0.03	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	3	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	0.46	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	0.64	mm	UL 94
UL Recognized, 94-5VA Rating	3	mm	UL 94
Oxygen Index (LOI)	30	%	ASTM D 2863
UV-light, water exposure /immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.