

# NORYL<sup>TM</sup> RESIN GFN3F

REGION ASIA

## DESCRIPTION

PPE+PS blend. 30% Glass reinforced. NSF 61 listing in several colors (restrictions apply). FDA compliance (restrictions apply). Low water absorption. Hydrolytic stability. Dimensional stability. Suitable for fluid engineering applications including pump housings, pump impellers and water meter components.

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, brk, Type I, 50 mm/min	130	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	9150	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	180	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	8000	MPa	ASTM D 790
Tensile Stress, break, 50 mm/min	110	MPa	ISO 527
Tensile Strain, break, 50 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	8500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	160	MPa	ISO 178
Flexural Modulus, 2 mm/min	6800	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	588	J/m	ASTM D 4812
Izod Impact, notched, 23°C	117	J/m	ASTM D 256
Izod Impact, notched, -30°C	124	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	20	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	31	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	11	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	147	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	142	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	137	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.06E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.18E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	143	°C	ISO 306
Vicat Softening Temp, Rate B/120	147	°C	ISO 306
HDT/af, 1.8 MPa Flatw 80*10*4 sp=64mm	137	°C	ISO 75/af
<b>PHYSICAL</b>			
Specific Gravity	1.29	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.1 – 0.4	%	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Flow Rate, 280°C/5.0 kgf	3.2	g/10 min	ASTM D 1238
Water Absorption, (23°C/sat)	0.1	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	2	cm <sup>3</sup> /10 min	ISO 1133
<b>INJECTION MOLDING</b>			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 325	°C	
Nozzle Temperature	300 – 325	°C	
Front - Zone 3 Temperature	290 – 325	°C	
Middle - Zone 2 Temperature	275 – 320	°C	
Rear - Zone 1 Temperature	265 – 315	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.