

LEXANTM RESIN 133R

REGION ASIA

DESCRIPTION

LEXAN 133R is the highest viscosity, UV stabilized, release containing, linear polycarbonate grade. Suitable for injection molding and extrusion processes. Available in transparent and multiple colors.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	62	MPa	SABIC - Japan Method
Tensile Strain, break	220 – 220	%	SABIC - Japan Method
Flexural Stress	93	MPa	ASTM D 790
Flexural Modulus	2200	MPa	ASTM D 790
Hardness, Rockwell R	123	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	833	J/m	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	135	°C	ASTM D 648
CTE, -30°C to 30°C	0.00007 – 0.00007	1/°C	TMA
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Water Absorption, 24 hours	0.15	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
ELECTRICAL			
Surface Resistivity	1.E+16	Ohm	ASTM D 257
Relative Permittivity, 50/60 Hz	3.2	-	ASTM D 150

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.