

NORYL™ RESIN V0150B

REGION ASIA

DESCRIPTION

NORYL V0150B is an unfilled, injection moldable modified polyphenylene ether resin.. Designed for high heat resistance and thin wall FR performance, this resin delivers a UL94 V0 rating at 1.5 mm and a UL94 5Va rating at 2.0 mm. NORYL V0150B is also halogen free according to VDE/DIN 472 part 815 and may be an excellent material candidate where flame resistance and high temperature resistance is required.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	70	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	60	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	7	%	ASTM D 638
Tensile Modulus, 5 mm/min	2500	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	105	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2550	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	35	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	70	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	10	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	110	MPa	ISO 178
Flexural Modulus, 2 mm/min	2400	MPa	ISO 178
Hardness, H358/30	113	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	330	J/m	ASTM D 256
Izod Impact, notched, -30°C	180	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	50	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	155	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ASTM E 831
Thermal Conductivity	0.27	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Ball Pressure Test, approximate maximum	140	°C	IEC 60695-10-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate A/50	160	°C	ISO 306
Vicat Softening Temp, Rate B/50	145	°C	ISO 306
Vicat Softening Temp, Rate B/120	155	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	140	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	130	°C	ISO 75/Ae
Relative Temp Index, Elec	110	°C	UL 746B
Relative Temp Index, Mech w/impact	105	°C	UL 746B
Relative Temp Index, Mech w/o impact	115	°C	UL 746B
PHYSICAL			
Specific Gravity	1.11	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	3.5	g/10 min	ASTM D 1238
Density	1.11	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.18	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 300°C/5.0 kg	10	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	33	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	26	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0009	-	IEC 60250
Dissipation Factor, 1 MHz	0.003	-	IEC 60250
Comparative Tracking Index	250	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.8	-	IEC 60250
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94-5VA Rating	2	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	775	°C	IEC 60695-2-13
Oxygen Index (LOI)	32	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 3	hrs	
Melt Temperature	300 – 320	°C	
Nozzle Temperature	280 – 300	°C	
Front - Zone 3 Temperature	300 – 320	°C	
Middle - Zone 2 Temperature	280 – 300	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Hopper Temperature	80 – 100	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	100 – 130	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.