

GELOY™ RESIN XP4045LG

REGION AMERICAS

DESCRIPTION

PC/ASA. Excellent weatherability, low gloss.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.2	%	ISO 527
Tensile Strain, break, 50 mm/min	46.7	%	ISO 527
Tensile Modulus, 1 mm/min	2320	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	93	MPa	ISO 178
Flexural Modulus, 2 mm/min	2270	MPa	ISO 178
IMPACT			
Instrumented Impact Energy @ peak, 23°C	45	J	ASTM D 3763
Instrumented Impact Energy @ peak, -30	15	J	ASTM D 3763
Instrumented Impact Total Energy, 23°C	53	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	17	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -40°C	8	kJ/m ²	ISO 180/1A
Charpy -40°C, V-notch Edgew 80*10*3 sp=62mm	12	kJ/m ²	ISO 179/1eA
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	25	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m ²	ISO 179/1eA
THERMAL			
CTE, -30°C to 80°C, flow	6.7E-05	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	7.6E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	126	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	125	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	103	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.9	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.6 – 0.9	%	SABIC method
Density	1.19	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 260°C/5.0 kg	28	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	265 – 285	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Nozzle Temperature	260 – 275	°C	
Front - Zone 3 Temperature	240 – 270	°C	
Middle - Zone 2 Temperature	250 – 275	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	50 – 80	°C	
Back Pressure	0.3 – 1	MPa	
Screw Speed	30 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.