

# NORYL<sup>TM</sup> RESIN RN0206

REGION ASIA

## DESCRIPTION

RN0206 is an unfilled Post Consumer Recycle (PCR) based injection moldable modified polyphenylene ether resin comprising at least 10% PCR styrenic series resin content. Available in black only.

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	73	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	14	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	100	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2500	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	180	J/m	ASTM D 256
<b>THERMAL</b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	118	°C	ASTM D 648
Ball Pressure Test, approximate maximum	120	°C	IEC 60695-10-2
<b>PHYSICAL</b>			
Specific Gravity	1.1	-	ASTM D 792
Melt Flow Rate, 250°C/10.0 kgf	5	g/10 min	ASTM D 1238
<b>ELECTRICAL</b>			
Dielectric Strength, in air, 3.2 mm	27	kV/mm	ASTM D 149
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-0 Flame Class Rating	0.75	mm	UL 94
<b>INJECTION MOLDING</b>			
Drying Temperature	105 – 110	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	275 – 305	°C	
Nozzle Temperature	275 – 305	°C	
Front - Zone 3 Temperature	265 – 305	°C	
Middle - Zone 2 Temperature	255 – 300	°C	
Rear - Zone 1 Temperature	245 – 295	°C	
Mold Temperature	70 – 100	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	
Vent Depth	0.038 – 0.051	mm	



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.