

VALOX™ FR RESIN ENH4550

REGION ASIA

DESCRIPTION

VALOX ENH4550 Polybutylene Terephthalate (PBT) resin is a 25% glass fiber reinforced, injection moldable grade. This non-chlorinated, non-brominated flame retardant PBT has a UL V0 rating. VALOX ENH4550 resin is a general purpose resin that is an excellent candidate for a wide variety of applications.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	115	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	115	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	10300	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	165	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	165	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	8800	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	112	MPa	ISO 527
Tensile Stress, break, 5 mm/min	112	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	10400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	175	MPa	ISO 178
Flexural Stress, break, 2 mm/min	175	MPa	ISO 178
Flexural Strain, break, 2 mm/min	2	%	ISO 178
Flexural Modulus, 2 mm/min	9200	MPa	ISO 178
Hardness, H358/30	174	MPa	ISO 2039-1
Hardness, Rockwell R	124	-	ISO 2039-2
IMPACT			
Izod Impact, unnotched, 23°C	550	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	525	J/m	ASTM D 4812
Izod Impact, notched, 23°C	70	J/m	ASTM D 256
Izod Impact, notched, 0°C	70	J/m	ASTM D 256
Izod Impact, notched, -30°C	65	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	6	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	35	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 23°C	8	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	8	kJ/m ²	ISO 179/2C

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy Impact, unnotched, 23°C	45	kJ/m²	ISO 179/2C
Charpy Impact, unnotched, -30°C	40	kJ/m²	ISO 179/2C
THERMAL			
Vicat Softening Temp, Rate A/50	215	°C	ASTM D 1525
Vicat Softening Temp, Rate B/50	205	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	220	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	205	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.43E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.1E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	2.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.1E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	2.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.48E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	Pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	208	°C	ISO 306
Vicat Softening Temp, Rate B/120	207	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	207	°C	ISO 75/Af
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	140	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.52	-	ASTM D 792
Filler Content	25	%	ASTM D 229
Mold Shrinkage on Tensile Bar, flow	0.1 – 0.5	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.1 – 0.5	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.6 – 1.2	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 1.1	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	25	g/10 min	ASTM D 1238
Melt Flow Rate, 265°C/5.0 kgf	27	g/10 min	ASTM D 1238
Density	1.52	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.23	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	18	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	18	cm³/10 min	ISO 1133
Melt Viscosity, 250°C, 1500 sec-1	210	Pa-s	ISO 11443
Melt Viscosity, 260°C, 1500 sec-1	160	Pa-s	ISO 11443
ELECTRICAL			
Volume Resistivity	1.E+15	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	21	kV/mm	ASTM D 149
Dielectric Strength, in oil, 0.8 mm	30	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	24	kV/mm	ASTM D 149

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Strength, in oil, 3.2 mm	20	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3.4	-	ASTM D 150
Dissipation Factor, 1 MHz	0.12	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	0	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	30	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	24	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	19	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dissipation Factor, 1 MHz	0.12	-	IEC 60250
Comparative Tracking Index	300	V	IEC 60112
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	0.3	mm	UL 94
UL Recognized, 94-5VA Rating	2.0	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	0.4	mm	IEC 60695-2-12
Glow Wire Flammability Index 960°C, passes at, by VDE	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 0.8 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm, by VDE	775	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	230 – 255	°C	
Front - Zone 3 Temperature	240 – 260	°C	
Middle - Zone 2 Temperature	235 – 250	°C	
Rear - Zone 1 Temperature	230 – 240	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.