

LNPTTM THERMOTUFTM COMPOUND RBX7245

DESCRIPTION

LNP THERMOTUF RBX7245 compound is based on Polycarbonate (PC) resin with 50% post-consumer recycle (PCR) content. Added features of this grade include: Non-Brominated & Non-Chlorinated Flame Retardant with excellent V-0 rating at 0.6mm.

GENERAL INFORMATION	
Features	Flame Retardant, Sustainable (Mechanical Recycling), Non Cl/Br flame retardant
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	63	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	46	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	75	%	ASTM D638
Tensile Modulus, 5 mm/min	2500	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	102	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	64	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	92	MPa	ISO 178
Flexural Stress, break, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	700	J/m	ASTM D256
Izod Impact, notched, 0°C	310	J/m	ASTM D256
Izod Impact, notched, -30°C	91	J/m	ASTM D256
Charpy Impact, notched, 23°C, 80*10*4mm, Cut	51	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 0°C, 80*10*4mm, Cut	9	kJ/m ²	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy Impact, notched, -30°C, 80*10*4mm, Cut	7	kJ/m ²	ISO 179/1eA
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	101	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	92	°C	ASTM D648
CTE, -40°C to 90°C, flow	6.0E-05	1/°C	ASTM E831
CTE, -40°C to 90°C, xflow	7.1E-05	1/°C	ASTM E831
CTE, -40°C to 90°C, flow	6.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 90°C, xflow	7.1E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	110	°C	ISO 306
Vicat Softening Temp, Rate B/120	116	°C	ISO 306
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.2	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.3 – 0.4	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽²⁾	0.4 – 0.5	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	18	g/10 min	ASTM D1238
Water Absorption, (23°C/saturated)	0.1	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	18	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 300°C/1.2 kg	29	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS ⁽³⁾			
UL Yellow Card Link	E207780-103823841	-	-
UL Recognized, 94V-2 Flame Class Rating	≥0.25	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥0.6	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 300	°C	
Nozzle Temperature	250 – 300	°C	
Front - Zone 3 Temperature	250 – 300	°C	
Middle - Zone 2 Temperature	240 – 290	°C	
Rear - Zone 1 Temperature	230 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 85	°C	
Vent Depth	0.03 - 0.075	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.