

LNPTM FARADEXTM COMPOUND WX08014

DESCRIPTION

LNP FARADEX WX08014 is a compound based on Polybutylene Terephthalate resin containing Stainless Steel Fiber, Flame Retardant. Added features include: EMI/RMI Shielding, Electrically Conductive, Flame Retardant.

TYPICAL PROPERTY VALUES

Revision 20200422

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 5 mm/min	44	MPa	ISO 527
Tensile Stress, break, 5 mm/min	43	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	79	MPa	ISO 178
Flexural Stress, break, 2 mm/min	78	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3.7	%	ISO 178
Flexural Modulus, 2 mm/min	3400	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	3	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	9.7E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.11E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	150	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	76	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow, 24 hrs	1.9	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	2.2	%	ISO 294
Density	1.64	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+02 – 1.E+03	Ohm	ASTM D 257
Shielding Effectiveness @ 3mm	45 – 55	dB	SABIC method
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating ⁽¹⁾	3	mm	UL 94 by SABIC-IP
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 260	°C	
Middle - Zone 2 Temperature	245 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Mold Temperature	80 – 100	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) UL rating shown here is based on internal measurements.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.