

# LNP™ VERTON™ COMPOUND MV00ASXP

MFX-700-10 HS  
REGION EUROPE

## DESCRIPTION

LNP VERTON\* MV00AS is a compound based on Polypropylene resin containing Long Glass. Added features of this material include: Chemically Coupled.

## TYPICAL PROPERTY VALUES

Revision 20180202

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, break	131	MPa	ASTM D 638
Tensile Strain, break	1.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	10440	MPa	ASTM D 638
Flexural Stress	187	MPa	ASTM D 790
Tensile Stress, break	141	MPa	ISO 527
Tensile Strain, break	1.7	%	ISO 527
Tensile Modulus, 1 mm/min	13870	MPa	ISO 527
Flexural Stress	214	MPa	ISO 178
Flexural Modulus	11140	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, notched, 23°C	208	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	13	J	ASTM D 3763
Multiaxial Impact	13	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	66	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	29	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
HDT, 1.82 MPa, 3.2mm, unannealed	157	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.36E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.57E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.37E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.58E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	164	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	160	°C	ISO 75/Af

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>PHYSICAL</b>			
Density	1.33	g/cm <sup>3</sup>	ASTM D 792
Wear Factor Washer	73	10 <sup>-10</sup> in <sup>5</sup> -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.34	-	ASTM D 3702 Modified: Manual
Static COF	0.52	-	ASTM D 3702 Modified: Manual
Density	1.33	g/cm <sup>3</sup>	ISO 1183
<b>MECHANICAL PROPERTIES</b>			
Flexural modulus	9340	MPa	ISO 178/1A
<b>INJECTION MOLDING</b>			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Melt Temperature	220 – 250	°C	
Front - Zone 3 Temperature	250 – 260	°C	
Middle - Zone 2 Temperature	245 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Mold Temperature	40 – 65	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.