

LNPTM STAT-LOYTM COMPOUND KX09024

KX09024

DESCRIPTION

LNP STAT-LOY KX09024 is a compound based on Polyacetal with reduced Resistivity. Added features include: Antistatic Properties

TYPICAL PROPERTY VALUES

Revision 20200313

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Strain, break, 5 mm/min	12	%	ISO 527
Tensile Modulus, 1 mm/min	1000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	48	MPa	ISO 178
Flexural Modulus, 2 mm/min	1400	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	9	kJ/m²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	1.44E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.59E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	136	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	67	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow	2.8	%	SABIC method
Density	1.27	g/cm³	ISO 1183
ELECTRICAL			
Volume Resistivity	1.E+08 – 1.E+10	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+08 – 1.E+10	Ohm	ASTM D 257
INJECTION MOLDING			
Drying Temperature	80	°C	
z.jg .cpc.duic		C	
Drying Time	4	hrs	
Drying Time	4	hrs	
Drying Time Melt Temperature	4 195 – 205	hrs °C	
Drying Time Melt Temperature Front - Zone 3 Temperature	4 195 – 205 200 – 210	hrs °C °C	
Drying Time Melt Temperature Front - Zone 3 Temperature Middle - Zone 2 Temperature	4 195 – 205 200 – 210 190 – 200	hrs °C °C	
Drying Time Melt Temperature Front - Zone 3 Temperature Middle - Zone 2 Temperature Rear - Zone 1 Temperature	4 195 - 205 200 - 210 190 - 200 175 - 190	hrs °C °C °C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.