

# NORYL GTX™ RESIN GTX820

REGION ASIA

## DESCRIPTION

GR 20%. Higher stiffness of 800000 psi (4000 MPa) flexural modulus. Excellent chemical and high heat resistance. Application: valves.

## TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	117	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	117	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	7	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	194	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	5960	MPa	ASTM D 790
Hardness, Rockwell R	119	-	ASTM D 785
<b>IMPACT</b>			
Izod Impact, notched, 23°C	80	J/m	ASTM D 256
Izod Impact, notched, -30°C	53	J/m	ASTM D 256
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	248	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	254	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	232	°C	ASTM D 648
CTE, -20°C to 150°C, flow	0.0000306 – 0.0000396	1/°C	ASTM E 831
<b>PHYSICAL</b>			
Specific Gravity	1.24	-	ASTM D 792
Density	1.245	g/cm <sup>3</sup>	ASTM D 792
Water Absorption, 24 hours	0.5	%	ASTM D 570
Moisture Absorption, 50% RH, 24 hrs	1	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.65 – 0.85	%	SABIC method
<b>INJECTION MOLDING</b>			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.07	%	
Minimum Moisture Content	0.02	%	
Melt Temperature	280 – 305	°C	
Nozzle Temperature	280 – 305	°C	
Front - Zone 3 Temperature	275 – 305	°C	
Middle - Zone 2 Temperature	270 – 305	°C	
Rear - Zone 1 Temperature	265 – 305	°C	
Mold Temperature	75 – 120	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.