

NORYL GTX™ RESIN GTX626

REGION AMERICAS

DESCRIPTION

Blowmolding and extrusion. High heat and chemical resistant.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	83	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	95	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2270	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	336	J/m	ASTM D 256
Izod Impact, notched, -30°C	122	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	31	J	ASTM D 3763
Instrumented Impact Energy @ peak, -30	36	J	ASTM D 3763
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	179	°C	ASTM D 648
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL			
Specific Gravity	1.09	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	1.3 – 1.4	%	SABIC method
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.49	mm	UL 94
EXTRUSION BLOW MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Drying Time (Cumulative)	16	hrs	
Melt Temperature (Parison)	275 – 290	°C	
Barrel - Zone 1 Temperature	270 – 280	°C	
Barrel - Zone 2 Temperature	270 – 280	°C	
Barrel - Zone 3 Temperature	270 – 280	°C	
Barrel - Zone 4 Temperature	270 – 280	°C	
Adapter - Zone 5 Temperature	275 – 290	°C	
Head - Zone 6 - Top Temperature	275 – 290	°C	
Head - Zone 7 - Bottom Temperature	275 – 290	°C	
Mold Temperature	80	°C	
Die Temperature	275 – 290	°C	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.