

# STAMAX™ 30YK270EE

PP LGF REINFORCED IMPACT MODIFIED

## DESCRIPTION

STAMAX™ 30YK270EE is a 30% long glass fiber reinforced low emission grade with improved impact and flow properties. The glass fibers are chemically coupled to the PP matrix, resulting in high stiffness and strength.

IMDS ID: 80929807

## TYPICAL PROPERTY VALUES

Revision 20250523

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
Density	1120	kg/m <sup>3</sup>	ISO 1183
Glass fibre content	30	%	ISO 3451
<b>MECHANICAL PROPERTIES <sup>(1)</sup></b>			
<b>Tensile modulus</b>			
at 23 °C	6200	MPa	ISO 527/1A
at 80 °C	4400	MPa	ISO 527/1A
<b>Tensile strength</b>			
at 23 °C	100	MPa	ISO 527/1A
at 80 °C	55	MPa	ISO 527/1A
<b>Tensile elongation at break</b>			
at 23 °C	2.4	%	ISO 527/1A
<b>Flexural Modulus</b>			
at 23 °C	6000	MPa	ISO 178
at 80 °C	4000	MPa	ISO 178
<b>Flexural strength</b>			
at 23 °C	150	MPa	ISO 178
at 80 °C	75	MPa	ISO 178
<b>Charpy Impact Strength Notched</b>			
at 23 °C	28	kJ/m <sup>2</sup>	ISO 179/1eA
at -30 °C	28	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Charpy impact unnotched</b>			
at 23 °C	60	kJ/m <sup>2</sup>	ISO 179/1eU
at -30 °C	75	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL PROPERTIES</b>			
<b>Heat deflection temperature</b>			
at 1.80 MPa (HDT/A)	158	°C	ISO 75/A
<b>Coeff. of linear thermal expansion</b>			
-30 °C to 100 °C	40	µm/mK	ISO 11359-2

(1) All measurements on injection molded samples.



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.