

FLEX NORYL™ RESIN WCV063

REGION ASIA

DESCRIPTION

Flexible, non-halogenated FR, mPPE extrusion grade material for evaluation in automotive wire coating applications requiring ISO6722.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	28	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	28	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	90	%	ASTM D 638
Tensile Modulus, 50 mm/min	840	MPa	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	720	MPa	ASTM D 790
Hardness, Shore D, 10S reading	63	-	ASTM D 2240
Tensile Stress, yield	25	MPa	ISO 527
Tensile Stress, break, 50 mm/min	25	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	20	%	ISO 527
Tensile Strain, break, 50 mm/min	50	%	ISO 527
Tensile Modulus, 1 mm/min	690	MPa	ISO 527
Flexural Modulus	790	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	560	J/m	ASTM D 256
Izod Impact, notched, -30°C	170	J/m	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	37	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	14	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	82	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	56	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	66	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.03	-	ASTM D 792
Melt Flow Rate, 280°C/5.0 kgf	33	g/10 min	ASTM D 1238
ELECTRICAL			
Relative Permittivity, 1 GHz	2.47	-	ASTM D 150
Dissipation Factor, 1 GHz	0.0032	-	ASTM D 150
WIRE COATING EXTRUSION			
Drying Temperature	80 – 100	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Extruder Length/Diameter Ratio (L/D)	>24:1	-	
Compression Ratio	2:1-3:1	-	
Screw Speed	5 – 60	rpm	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Feed Zone Temperature	200 – 260	°C	
Middle Zone Temperatures	270 – 300	°C	
Head Zone Temperature	280 – 300	°C	
Neck Temperature	280 – 300	°C	
Cross-head Temperature	280 – 300	°C	
Die Temperature	280 – 300	°C	
Melt Temperature	280 – 300	°C	
Conductor Pre-heat Temperature	100 – 150	°C	
Screen Pack	60/200/60	-	
Cooling Water Air Gap	100 – 1000	mm	
Water Bath Temperature	15 – 30	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.