

NORYL™ RESIN PX0844

REGION ASIA

DESCRIPTION

PPE+PS blend. Unfilled. UL94 HB rated. Low water absorption. Hydrolytic stability. Dimensional stability.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	49	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	42	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	75	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2240	MPa	ASTM D 790
Hardness, Rockwell R	114	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	234	J/m	ASTM D 256
Izod Impact, notched, -40°C	133	J/m	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	121	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	112	°C	ASTM D 648
CTE, 0°C to 100°C, flow	7.38E-05	1/°C	ASTM E 831
PHYSICAL			
Specific Gravity	1.06	-	ASTM D 792
Water Absorption, 24 hours	0.1	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
INJECTION MOLDING			
Drying Temperature	105 – 110	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	275 – 305	°C	
Nozzle Temperature	275 – 305	°C	
Front - Zone 3 Temperature	265 – 305	°C	
Middle - Zone 2 Temperature	255 – 300	°C	
Rear - Zone 1 Temperature	245 – 295	°C	
Mold Temperature	70 – 100	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	
Vent Depth	0.038 – 0.051	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.