

NORYL™ RESIN EN265

REGION AMERICAS

DESCRIPTION

Extrusion grade. 254F (123C) DTUL. UL94 V-1 rated.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	63	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	25	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	99	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2550	MPa	ASTM D 790
Hardness, Rockwell R	119	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	186	J/m	ASTM D 256
Izod Impact, notched, -40°C	133	J/m	ASTM D 256
Gardner, -30°C	14	J	ASTM D 3029
Gardner, -40°C	4	J	ASTM D 3029
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	123	°C	ASTM D 648
CTE, -40°C to 95°C, flow	5.94E-05	1/°C	ASTM E 831
Relative Temp Index, Elec	110	°C	UL 746B
Relative Temp Index, Mech w/impact	105	°C	UL 746B
Relative Temp Index, Mech w/o impact	110	°C	UL 746B
PHYSICAL			
Specific Gravity	1.08	-	ASTM D 792
Water Absorption, 24 hours	0.07	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	19.6	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	2.69	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0007	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94V-1 Flame Class Rating	1.49	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	5.99	mm	UL 94
Oxygen Index (LOI)	29.2	%	ASTM D 2863
Radiant Panel Listing	RP100	-	UL Tested
UV-light, water exposure/immersion	F1	-	UL 746C
EXTRUSION			
Drying Temperature	105 – 115	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	–	%	
Melt Temperature	225 – 255	°C	
Barrel - Zone 1 Temperature	205	°C	
Barrel - Zone 2 Temperature	205	°C	
Barrel - Zone 3 Temperature	225	°C	
Barrel - Zone 4 Temperature	225	°C	
Adapter Temperature	250	°C	
Die Temperature	250	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.