

NORYL™ RESIN FE1520PW

REGION ASIA

DESCRIPTION

Noryl® FE1520PW resin is a blend of polyphenylene ether (PPE) and polystyrene (PS) resin that contains 20% glass reinforcement. The resin is suitable for injection molding. Noryl FE1520PW resin has been developed for fluid engineering applications that require improved hydrolytic stability. Noryl FE1520PW resin has been certified for potable water applications up to 85C in Europe and North America in limited colors.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	119	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	7100	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	175	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	6970	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	65	mg/1000cy	SABIC method
Tensile Stress, break, 5 mm/min	119	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.6	%	ISO 527
Tensile Modulus, 1 mm/min	7170	MPa	ISO 527
Flexural Stress, break, 2 mm/min	165	MPa	ISO 178
Flexural Modulus, 2 mm/min	6040	MPa	ISO 178
Hardness, H358/30	220	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched, 23°C	400	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	395	J/m	ASTM D 4812
Izod Impact, notched, 23°C	65	J/m	ASTM D 256
Izod Impact, notched, -30°C	45	J/m	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	23	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	4	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	6	kJ/m ²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, -30°C	27	kJ/m ²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	30	kJ/m ²	ISO 179/1eU
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate A/50	150	°C	ISO 306
Vicat Softening Temp, Rate B/120	144	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	139	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	132	°C	ISO 75/Ae
PHYSICAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, 50% RH, equilib	0.06	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.4	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.3 – 0.6	%	SABIC method
Density	1.24	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.2	%	ISO 62
Melt Volume Rate, MVR at 280°C/10.0 kg	22	cm ³ /10 min	ISO 1133
INJECTION MOLDING ⁽¹⁾			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	290 – 320	°C	
Nozzle Temperature	290 – 320	°C	
Front - Zone 3 Temperature	300 – 310	°C	
Middle - Zone 2 Temperature	280 – 300	°C	
Rear - Zone 1 Temperature	270 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 120	°C	

(1) For detailed processing conditions please contact the SABIC representative.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.