

NORYL™ RESIN EXNLO357

REGION AMERICAS

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	63	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	51	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.1	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	29.3	%	ASTM D 638
Tensile Modulus, 5 mm/min	2160	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	103	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2630	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	64	MPa	ISO 527
Tensile Stress, break, 50 mm/min	53	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.9	%	ISO 527
Tensile Strain, break, 50 mm/min	20.7	%	ISO 527
Tensile Modulus, 1 mm/min	2900	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	107	MPa	ISO 178
Flexural Modulus, 2 mm/min	2620	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	169	J/m	ASTM D 256
Izod Impact, notched, -30°C	92	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	34	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	15	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	136	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	114	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.39E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.12E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.12E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.39E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	136	°C	ISO 306
Vicat Softening Temp, Rate B/120	138	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	116	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.08	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.8	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	9.5	g/10 min	ASTM D 1238
Density	1.08	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.25	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Volume Rate, MVR at 280°C/5.0 kg	9	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	105 – 110	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	280 – 310	°C	
Nozzle Temperature	280 – 310	°C	
Front - Zone 3 Temperature	270 – 310	°C	
Middle - Zone 2 Temperature	260 – 305	°C	
Rear - Zone 1 Temperature	250 – 300	°C	
Mold Temperature	75 – 105	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.