

LNPTM ELCRESTM DMX1435D

REGION ASIA

DESCRIPTION

LNPTM ELCRESTM DMX1435D is a UV stabilized standard flow polycarbonate copolymer resin with diffusion effect and improved scratch resistance, which is a good candidate for Consumer Electronics, mobility interiors and other adjacent applications, which need lower scratch and diffusive effects performance.

TYPICAL PROPERTY VALUES

Revision 20200423

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	77	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	60	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7.5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	20	%	ASTM D 638
Tensile Modulus, 50 mm/min	2700	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	120	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2500	MPa	ASTM D 790
Hardness, Rockwell L	110	-	ASTM D 785
Hardness, Rockwell M	90	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	77	MPa	ISO 527
Tensile Stress, break, 50 mm/min	59	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7	%	ISO 527
Tensile Strain, break, 50 mm/min	20	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	110	MPa	ISO 178
Flexural Modulus, 2 mm/min	2600	MPa	ISO 178
Pencil Hardness test, 1kgf	H	-	ASTM D 3363
IMPACT			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D 4812
Izod Impact, notched, 23°C	30	J/m	ASTM D 256
Izod Impact, notched, -30°C	30	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	7	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	40	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	2.2	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	2.0	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	2.2	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	2.5	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	46	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	138	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	129	°C	ASTM D 648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	115	°C	ASTM D 648
CTE, -40°C to 95°C, flow	7E-05	1 / °C	ASTM E 831
CTE, -40°C to 95°C, xflow	7E-05	1 / °C	ASTM E 831
CTE, 23°C to 80°C, flow	7E-05	1 / °C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7E-05	1 / °C	ISO 11359-2
Vicat Softening Temp, Rate B/50	136	°C	ISO 306
Vicat Softening Temp, Rate B/120	138	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	129	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	115	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.18	-	ASTM D 792
Specific Volume	0.85	cm ³ /g	ASTM D 792
Density	1.17	g/cm ³	ASTM D 792
Water Absorption, 24 hours	0.08	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.28	%	ASTM D 570
Water Absorption, 50% RH, equilib	0.13	%	ASTM D 570
Moisture Absorption, 50% RH, 24 hrs	0.04	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	15.4	g/10 min	ASTM D 1238
Density	1.18	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.27	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.13	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	14	cm ³ /10 min	ISO 1133
OPTICAL			
Light Transmission at 2.0 mm	85	%	ASTM D1003
Haze, 2mm	85	%	SABIC method
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-104234328	-	-
UL Recognized, 94HB Flame Class Rating	≥0.6	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	70 – 95	°C	

⁽¹⁾ UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.