

LNPT™ FARADEX™ COMPOUND DS0036I

DS-1003 FR HI
REGION EUROPE

DESCRIPTION

LNP FARADEX DS0036I is a compound based on Polycarbonate resin containing 15% Stainless Steel. Added features of this material include: Electrically Conductive, EMI/RFI Shielding, High Impact, Non-Brominated & Non-Chlorinated Flame Retardant.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	59	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	53	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	5.1	%	ASTM D 638
Tensile Modulus, 5 mm/min	2550	MPa	ASTM D 638
Tensile Stress, yield, 5 mm/min	57	MPa	ISO 527
Tensile Stress, break, 5 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.8	%	ISO 527
Tensile Strain, break, 5 mm/min	4 – 8	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2600	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	1790	J/m	ASTM D 4812
Izod Impact, notched, 23°C	124	J/m	ASTM D 256
Multiaxial Impact	29	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	5.7E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	6.8E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	136	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	125	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.4 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 24 hrs	0.4 – 0.6	%	ISO 294
Density	1.29	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	0.13	%	ISO 62-1
ELECTRICAL			
Volume Resistivity	10000 – 1000000	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+02 – 1.E+04	Ohm	ASTM D 257
Static Decay, 5000V to <50V	0.01	< seconds	FTMS101B
Shielding Effectivness @ 3mm	40 – 55	dB	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	2	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	95 – 120	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.